



SiMP®-SEAL 65

Primerless windshield adhesive for elastic structural bonding.
Free of solvent and isocyanates

1

Description

SiMP®Seal 65 is a Primerless elastic adhesive based on Silyl-Terminated Polymer specifically studied for the windshield replacement aftermarket of inorganic and organic glass. Formulated with a high viscosity which confer to the product an excellent high initial tack. It combines very high holding power to excellent mechanical cohesion properties.

Areas of Application

Direct glazing and general structural elastic bonding adhesive. The high green strength and non-sag properties make it ideal for quick bonding of windscreen, side and rear windows on vehicle bodies. Equally suitable for structural elastic bonding, assembly of various materials exposed to high thermal and dynamic stress, in the transportation Industry (coach, caravan, refrigerated vehicles, containers) and marine.

Advantages

- Primerless adhesion to glass (inorganic and organic), metals and plastics
- Non-conductive and non-corrosive
- Non-sag consistency - Exceptional thixotropy
- Excellent weathering resistance - extremely good colour stability and UV resistance Free from
- Vibration and sound damping properties
- Highest green strength (high initial tack) values
- Highest mechanical properties.
- Free from Isocyanates, Silicone, Solvents and PVC
- Odourless
- No Hazard symbol required



ISO 9001

DESIGN AND PRODUCTION
BY CERTIFIED QUALITY SYSTEM
UNI EN ISO 9001:2008



NPT S.r.l.
NEW POLYURETHANE TECHNOLOGIES

Via G. Pansa, 2 - Loc. Crespelliano - 40053 Valsamoggia - BO - Italy
Ph. +39.051.969109 - Fax +39.051.969897
e-mail: csosimp@csosimp.com - web: www.csosimp.com
p.iva 01608281206 - c.f. 01553270180



Technical data

Appearance	Thixotropic paste
Colour	Black
Chemical nature	SiMP - Silyl Terminated Polymer
Curing Mechanism	Moisture-curing
Curing through volume [mm] (after 1 day at 23°C and 50% r.h.)	Ca. 3.0
Shore A hardness [N/mm²] (DIN 53505)	Ca. 68
Density [g/cc] (NPT method 06)	1,60 ± 0,02
Tack-free time [min] (23°C and 50% r.h.)	Ca. 20
Elastic modulus at 100% [N/mm²] (ISO 37 DIN 53504)	Ca. 3.2
Tensile strength [N/mm²] (ISO 37 DIN 53504)	Ca. 3.4
Elongation [%] (ISO 37 DIN 53504)	Ca. 120
Tear strenght [kN/m] (ISO 34-1 method B with nick)	Ca. 10
Application temperature [°C]	from +5 to +40
Temperature Resistance [°C]	-40/+100



ISO 9001

DESIGN AND PRODUCTION
BY CERTIFIED QUALITY SYSTEM
UNI EN ISO 9001:2008



NPT S.r.l.
NEW POLYURETHANE TECHNOLOGIES

Via G. Pansa, 2 - Loc. Crispellario - 40053 Valsamoggia - BO - Italy
Ph. +39.051.969109 - Fax +39.051.969897
e-mail: ecosimp@ecosimp.com - web: www.ecosimp.com
p.iva 01608281206 - c.f. 01553270180



Application

Surfaces must be clean, dry, free of water, oil, grease or rust and of sound quality. Remove all loose particles or residues with a jet of compressed air, sandpaper or hard brush. Glass, metal and other non-porous surfaces must be free of any coatings and wiped clean with solvent. Cleaners and/or primers may be required to achieve optimal adhesion.

Cleaning of equipment

Clean tools with acetone or alcohol immediately after use. Cured material can only be removed mechanically.

Personal protective measures

Keep out of reach of children. If skin contact occurs, remove immediately and wash with soap and water

Packaging

PE-cartridge 290ml:	12 cartridges per box
Alu- bags 400 ml.	12 bags per box (on request)
Alu- bags 600 ml.	20 bags per box

Storage

SiMP®Seal 65 can be stored for 12 months in its original packing (unopened container) at 5°- 25°C in a cool, dry place. The storage temperature should not exceed 25°C for extended periods of time. Keep away from wet areas, direct sunlight and heat sources.

General Information

The information contained in this technical data sheet is to the best of our knowledge correct, being based on our knowledge and experience to date and cannot be used as a guarantee, due to the various different materials present on the market and the fact that the application conditions are not under our direct control and supervision. NPT srl, however, guarantees constant product quality. NPT srl, has the right to modify or up-date this technical data sheet according to requirements. Customers are kindly requested to verify that they are in possession of the latest version.

ALWAYS CONSULT THE MATERIAL SAFETY DATA SHEET BEFORE USING THE PRODUCT.



ISO 9001

DESIGN AND PRODUCTION
BY CERTIFIED QUALITY SYSTEM
UNI EN ISO 9001:2008



NPT S.r.l.
NEW POLYURETHANE TECHNOLOGIES

Via G. Pansa, 2 - Loc. Crispellano - 40053 Valsamoggia - BO - Italy
Ph. +39.051.969109 - Fax +39.051.969897
e-mail: ecostimp@ecostimp.com - web: www.ecostimp.com
p.iva 01608281206 - c.f. 01553270180